

7
"PATENT"

PATENT APPLICATION TRANSMITTAL FORM

12/08/97
JCS59 U.S. PAT. & TM. OFF.
ASSISTANT COMMISSIONER FOR PATENTS
BOX PATENT APPLICATION
Washington, D.C. 20231

Attorney Docket No. 97U001

Sir:

- [X] "Express Mail" mailing label number EM539972442US. Date of Deposit December 8, 1997.
This correspondence is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

Transmitted herewith for filing is the patent application of

Inventor(s): Moses O. Jejelowo, Sun-Chueh Kao
For: Polymerization Catalyst System And Their Use

Enclosed are:

- [X] Specification and Claims with Declaration;
[] Specification and Claims without Declaration;
[] _____ sheets of informal drawings;
[] _____ sheets of formal drawings;
[X] An assignment of the invention to Exxon Chemical Patents Inc.;
[X] Information Disclosure Statement, Form - 1449;
[X] Copies of citations as listed on attached Form - 1449;
[X] Address all future communications to Exxon Chemical Company, Law Technology, P. O. Box 2149, Baytown, Texas 77522.
[] The certified copy of a priority application;
[] Priority of application Serial No. _____ Filed on _____ in _____ is claimed under 35 U.S.C. § 119(a)-(d).
[] Priority of provisional application Serial No. _____ Filed on _____ is claimed under 35 U.S.C. § 119(e)(1)-(2).
[X] The Filing Fee is calculated below.

CLAIMS AS FILED					
	(1) For	(2) Number Filed	(3) Number Extra	(4) Rate	(5) Basic Fee \$790.00
	Total Claims	50 - 20 =	30	x \$22.00	660.00
	Ind. Claims	7 - 3 =	4	x \$82.00	328.00
	Multiple Dependent Claim Fee		0	\$260.00	--
	TOTAL FILING FEE				\$1,778.00

Attorney Docket No. 97U001

[X] Please charge my Deposit Account No. 05-1715 in the amount of \$ 1,778.00.

[X] The Commissioner is hereby authorized to charge any additional fees which may be required during the entire pendency of the application, or credit any overpayment, to Deposit Account No. 05-1715. A duplicate copy of this Form is enclosed.

8 Dec. 1997

Date of Signature

Jaime Sher
Attorney or Agent

Jaime Sher

Registration No. 34,726

Telephone No. (281) 834-1832

Facsimile No. (281) 834-2495

Post Office Address (to which correspondence is to be sent):

Exxon Chemical Company

Law Technology

P. O. Box 2149

Baytown, Texas 77522-2149

08586596-120897

POLYMERIZATION CATALYST SYSTEMS AND THEIR USE

FIELD OF THE INVENTION

5 This invention relates to catalysts, catalyst systems and their use in olefin polymerization. The invention more particularly relates to substituted hafnium metallocene-type catalyst compounds, catalyst systems thereof and their use in a polymerizing process.

BACKGROUND OF THE INVENTION

10 The use of bulky ligand transition metal catalyst compounds in polymerization processes to produce a diverse array of new polymers for use in a wide variety of applications and products is well known in the art. Typical bulky ligand transition metal compounds, known as metallocene-type compounds, are generally described as containing one or more ligands capable of η -5 bonding to the transition metal atom, usually, cyclopentadienyl derived ligands or moieties, in
15 combination with a transition metal selected from Group 4, 5 or 6 or from the lanthanide and actinide series of the Periodic Table of Elements. Predominantly in the literature the transition metal is from Group 4, particularly either titanium, zirconium or hafnium, and the cyclopentadienyl derived ligand or moiety is substituted with various radicals, typically alkyl radicals, or two or more
20 cyclopentadienyl ligands are joined by a structural bridge, usually an organic or inorganic group, typically, a carbon or silicon atom containing group.

Other forms of these metallocene-type catalyst compounds contain a cyclopentadienyl derived ligand or moiety and a heteroatom containing group bonded to a transition metal, typically titanium, where the cyclopentadienyl ligand
25 or moiety and the heteroatom containing group are joined by a structural bridge, usually a silicon atom containing group. These and other metallocene-type catalyst compounds in combination with an activator form metallocene-type catalyst systems capable of polymerizing various olefin(s), alone or in combination with other olefin(s). Exemplary of the development of these and other metallocene-type
30 catalyst compounds and catalyst systems are described in U.S. Patent Nos. 5,017,714, 5,055,438, 5,096, 867, 5,198,401, 5,229,478, 5,264,405, 5,278,119, 5,324,800, 5,384,299, 5,408,017, 5,491,207 and 5,621,126 all of which are herein fully incorporated by reference.

35 It is well known in the art, although not fully understood, that where the transition metal of these metallocene-type catalyst compounds is hafnium, often

08986696.120897

referred to as a "hafnocene", hafnocene catalyst systems generally, among other characteristics, perform relatively poorly in comparison to their titanium, especially their zirconium equivalents, often referred to as "zirconocenes". Although hafnocenes will typically polymerize polymers having higher molecular weights than their zirconocene equivalents under similar polymerization conditions, their overall poor activity make them inferior polymerization catalysts. For example, European patent EP 0 284 707 B1 granted August 30, 1995, which is fully incorporated herein by reference, describes a process for polymerizing olefins using a catalyst system, in liquid form, containing a chiral, sterorigid bridged hafnium metallocene catalyst compound and an aluminum compound.

Thus, it would be highly advantageous to have a hafnium metallocene-type catalyst system capable of polymerizing olefin(s) with improved catalyst performance.

SUMMARY OF THE INVENTION

This invention relates to a substituted bulky ligand hafnium transition metal metallocene-type catalyst compound and a catalyst system thereof. The invention also relates to a polymerization process for polymerizing one or more olefin(s) utilizing the substituted bulky ligand hafnium transition metal metallocene-type catalyst compound.

In one embodiment, the invention provides for a catalyst system of a bulky ligand hafnium metallocene-type compound where at least one bulky ligand is substituted with a substituent having at least 3 or more non-hydrogen atoms, and an activator. Preferably, the bulky ligand is substituted with a substituent having at least 3 or more carbon atoms or silicon atoms or combinations thereof.

In a preferred embodiment, the invention provides for an activated catalyst system of a bulky ligand hafnium metallocene-type catalyst complex where the bulky ligand is capable of η -5 bonding to the hafnium transition metal and is substituted with an alkyl substituent having 3 or more carbon atoms, preferably where the alkyl substituent has 3 to 5 carbon atoms, more preferably the alkyl substituent is a linear alkyl. In one preferred embodiment, the alkyl substituent is at least one n-butyl group, most preferably at least one n-propyl group, substituted to at least one of the bulky ligands.

In yet another embodiment, the invention is directed to a process for polymerizing, preferably in a continuous process, one or more monomer(s) in the presence of the catalyst system or activated catalyst complex described above.

In one preferred embodiment, the above process of the invention is a continuous slurry or gas phase polymerization process.

In another embodiment, the invention is directed to a polymer product produced using the hafnocene catalyst systems or complexes described above, wherein the polymer product contains less than 2 ppm hafnium, preferably less than 1 ppm hafnium.


DETAILED DESCRIPTION OF THE INVENTION

Introduction

The invention is directed toward a hafnium transition metal metallocene-type catalyst system for polymerizing one or more olefin(s). It has been surprisingly discovered that by properly substituting the cyclopentadienyl derived ligand or moiety of a hafnocene results in an improved catalyst system. Unexpectedly where the substituent on the bulky ligand or moiety is a substituent having 3 or more non-hydrogen atoms, preferably 3 or more carbon atoms, preferably an alkyl substituent, for example n-propyl or n-butyl, the catalyst activity of the hafnocene metallocene-type catalyst system is substantially improved. Along with a sufficiently commercially acceptable activity, the hafnocene catalyst systems of the invention produces polymers having higher molecular weights in comparison to its zirconocene equivalents at the same or similar polymerization conditions. It was surprising that the substituted hafnocene of the invention will tend to produce lower density polymer products than its zirconocene equivalent at substantially the same molecular weight.

Catalyst Components and Catalyst Systems

Preferred metallocene catalysts of the invention, for example, are typically those bulky ligand transition metal complexes described by formula (I):



where L is a substituted bulky ligand bonded to M, p is the anionic charge of L and m is the number of L ligands and m is 1, 2 or 3; at least one L is substituted with at least one substituent having 3 or more non-hydrogen atoms, preferably having 3 or more carbon atoms or silicon atoms or combination thereof; A is a ligand bonded to M and capable of inserting an olefin between the M-A bond, q is the anionic charge of A and n is the number of A ligands and n is 1, 2, 3 or 4, M is the transition metal hafnium (Hf), and $(p \times m) + (q \times n) + k$ corresponds to the formal oxidation state of the metal center; where k is the charge on the cation and k is 1, 2, 3 or 4, and B' is a chemically stable, non-nucleophilic anionic complex,

preferably having a molecular diameter of 4 Å or greater and j is the anionic charge on B' , h is the number of cations of charge k , and i the number of anions of charge j such that $h \times k = j \times i$.

Any two L and/or A ligands may be bridged to each other and/or
unbridged. The catalyst compound may be full-sandwich compounds having two or
more ligands L, which include cyclopentadienyl derived ligands or substituted
cyclopentadienyl derived ligands, or half-sandwich compounds having one ligand
L, which is a cyclopentadienyl derived ligand or heteroatom substituted
cyclopentadienyl derived ligand or hydrocarbyl substituted cyclopentadienyl
derived ligand or moiety such as an indenyl ligand, a benzindenyl ligand or a
fluorenyl ligand and the like including hydrogenated versions thereof or any other
ligand capable of η -5 bonding to the transition metal atom. One or more of these
bulky ligands is π -bonded to the transition metal atom. At least one L is
substituted with at least one substituent having 3 or more non-hydrogen atoms,
preferably having 3 or more carbon atoms or 3 or more non-hydrogen atoms of
which at least one is a silicon atom; in addition, L can be substituted with a
combination of additional substituents, which can be the same or different. Non-
limiting examples of non-hydrogen atoms include silicon, germanium, tin, oxygen,
nitrogen or carbon and combinations thereof. Non-limiting examples of additional
substituents include hydrogen or a linear, branched or cyclic alkyl, alkenyl or aryl
radical or combination thereof having from 1 to 30 carbon atoms. The at least one
substituent or the additional substituents can also be substituted with hydrogen or a
linear, branched or cyclic alkyl, alkenyl or aryl radical having from 1 to 30 carbon
atoms or non-hydrogen atoms. L may also be other types of bulky ligands
including but not limited to bulky amides, phosphides, alkoxides, aryloxides,
imides, carbolides, borollides, porphyrins, phthalocyanines, corrins and other
polyazomacrocycles. Other ligands may be bonded to the hafnium transition metal,
such as a leaving group, such as but not limited to weak bases such amines,
phosphines, ether and the like. In addition to the transition metal, these ligands
may be optionally bonded to A or L. Non-limiting examples of catalyst
components and catalyst systems are discussed in for example, U.S. Patent Nos.
4,530,914, 4,871,705, 4,937,299, 5,124,418, 5,017,714, 5,120,867, 5,210,352,
5,278,264, 5,278,119, 5,304,614, 5,324,800, 5,347,025, 5,350,723, 5,391,790,
5,391,789, 5,399,636, 5,539,124, 5,455,366, 5,534,473, 5,684,098 and 5,693,730
all of which are herein fully incorporated by reference. Also, the disclosures of

European publications EP-A-0 591 756, EP-A-0 520 732, EP-A- 0 420 436, EP-B1 0 485 822, EP-B1 0 485 823 and EP-A2-0 743 324 and PCT publications WO 91/04257, WO 92/00333, WO 93/08221, WO 93/08199, WO 94/01471, WO 96/20233, WO 97/15582 and WO 97/19959 are all herein fully incorporated by reference.

In one embodiment, the activated catalyst of the invention is formed from a hafnocene catalyst compound represented by the general formula (II):



where L is a bulky ligand substituted with at least one substituent having 3 or more non-hydrogen atoms, preferably 3 or more carbon atoms, preferably an alkyl substituent having 3 or more carbon atoms, even more preferably a linear alkyl substituent having 3 or more carbon atoms, M is Hf, A, and p, m, q and n are as defined above and E is an anionic leaving group such as but not limited to hydrocarbyl, hydride, halide or combination thereof or any other anionic ligands; r is the anionic charge of E and o is the number of E ligands and o is 1, 2, 3 or 4 such that $(p \times m) + (q \times n) + (r \times o)$ is equal to the formal oxidation state of the metal center; and an aluminum alkyl, alumoxane, modified alumoxane or any other oxy-containing organometallic compound or non-coordinating ionic activators, or a combination thereof.

In one embodiment of the invention the substituted hafnocene catalyst compound of the invention includes monocyclopentadienyl heteroatom containing hafnium transition metal metallocene-type compounds. This metallocene-type compound is activated by either an alumoxane, modified alumoxane, a non-coordinating ionic activator, a Lewis acid or a combination thereof to form an active polymerization catalyst system. These types of catalyst systems are described in, for example, PCT publication WO 92/00333, WO 94/07928, WO 91/04257, WO 94/03506, WO96/00244 and WO 97/15602 and U.S. Patent Nos. 5,057,475, 5,096,867, 5,055,438, 5,198,401, 5,227,440 and 5,264,405 and European publication EP-A-0 420 436, all of which are herein fully incorporated by reference. Additionally it is within the scope of this invention that the metallocene catalysts and catalyst systems may be those described in U.S. Patent Nos. 5,064,802, 5,145,819, 5,149,819, 5,243,001, 5,239,022, 5,276,208, 5,296,434, 5,321,106, 5,329,031, 5,304,614 and 5,677,401, and PCT publications WO 93/08221, WO 93/08199 and WO 95/07140 and European publications EP-A-


0 578 838 and EP-A-0 638 595 all of which are herein fully incorporated by reference.

In another embodiment, the catalyst component is represented by the formula (III):



wherein M is a Hf transition metal, $(C_5H_{5-d-f}R''_d)_e$ is an unsubstituted or substituted cyclopentadienyl ligand bonded to M, wherein at least one $(C_5H_{5-d-f}R''_d)$ has at least one R'' that is an alkyl substituent having 3 or more carbon atoms, each additional R'' , which can be the same or different is hydrogen or a substituted or unsubstituted hydrocarbyl having from 1 to 30 carbon atoms or combinations thereof or two or more carbon atoms are joined together to form a part of a substituted or unsubstituted ring or ring system having 4 to 30 carbon atoms, R''' is one or more or a combination of carbon, germanium, silicon, phosphorous or nitrogen atoms containing radical bridging two $(C_5H_{5-d-f}R''_d)$ rings, or bridging one $(C_5H_{5-d-f}R''_d)$ ring to M; each Q which can be the same or different is a hydride, substituted or unsubstituted hydrocarbyl having from 1 to 30 carbon atoms, halogen, alkoxides, aryloxides, amides, phosphides or any other univalent anionic ligand or combination thereof; also, two Q's together form an alkylidene ligand or cyclometallated hydrocarbyl ligand or other divalent anionic chelating ligand, where g is an integer corresponding to the formal oxidation state of M, d is 0, 1, 2, 3, 4 or 5, f is 0 or 1 and e is 1, 2 or 3.

In another preferred embodiment of this invention the catalyst component is represented by the formula (IV):



wherein M is Hf; $(C_5H_{5-y-x}R_x)$ is a cyclopentadienyl ring which is substituted with from at least one to 5 substituent groups R, "x" is 1, 2, 3, 4 or 5 denoting the degree of substitution, and at least one R is a non-hydrogen atom, preferably R is at least 3 carbon atoms or silicon atoms or a combination thereof, more preferably R is an alkyl having 3 or more carbon atoms, for example n-propyl or n-butyl, and each additional substituent group R is, independently, a radical selected from a group consisting of C_1 - C_{20} hydrocarbyl radicals, substituted C_1 - C_{20} hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen atom, C_1 -

C₂₀ hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group 14 of the Periodic Table of Elements, and halogen radicals or (C₅H_{5-y-x}R_x) is a cyclopentadienyl ring in which two adjacent R-groups are joined forming C₄-C₂₀ ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl;

(JR'_{z-1-y}) is a heteroatom ligand in which J is an element with a coordination number of three from Group 15 or an element with a coordination number of two from Group 16 of the Periodic Table of Elements, preferably nitrogen, phosphorus, oxygen or sulfur with nitrogen being preferred, and each R' is, independently a radical selected from a group consisting of C₁-C₂₀ hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen atom, y is 0 or 1, and "z" is the coordination number of the element J;

each Q is, independently any univalent anionic ligand such as halogen, hydride, or substituted or unsubstituted C₁-C₃₀ hydrocarbyl, alkoxide, aryloxy, amide or phosphide, provided that two Q may be an alkylidene, a cyclometallated hydrocarbyl or any other divalent anionic chelating ligand;

A is a covalent bridging group containing a Group 15 or 14 element such as, but not limited to, a dialkyl, alkylaryl or diaryl silicon or germanium radical, alkyl or aryl phosphine or amine radical, or a hydrocarbyl radical such as methylene, ethylene and the like;

L' is a Lewis base such as diethylether, tetraethylammonium chloride, tetrahydrofuran, dimethylaniline, aniline, trimethylphosphine, n-butylamine, and the like; and w is a number from 0 to 3. Additionally, L' may be bonded to any of R, R' or Q.

In one embodiment of the bulky ligand hafnium transition metal metallocene-type catalyst compounds described above, at least one bulky ligand is substituted with a substituent having 3 or more carbon atoms, preferably 3 to 20 carbon atoms, more preferably 3 to 10 and most preferably 3 to 5 carbon atoms. In another preferred embodiment, the hafnium transition metal metallocene-type catalyst system has two bulky ligands that are each substituted with a linear or branched, preferably linear, alkyl having 3 or more carbon atoms, preferably 3 to 10 carbon atoms, most preferably 3 to 5 carbon atoms, where at least one bulky ligand is a cyclopentadienyl derived ligand, preferably a cyclopentadienyl ring. In a preferred embodiment the bulky ligands of the hafnium transition metal

08986696.1.2097
258021.9698680

metallocene are both cyclopentadienyl rings at least one of which is substituted with one or more branched or linear alkyls having 3 or more carbon atoms, preferably both cyclopentadienyl rings are substituted with at least one n-propyl, isopropyl, n-butyl, isobutyl, n-pentyl, or combination thereof. In a more preferred embodiment the hafnium transition metal metallocene-type catalyst compound has two bulky ligands that are each substituted with n-propyl, n-butyl or n-pentyl or combination thereof, in the same or different positions, preferably in the same position on the bulky ligands.

In another preferred embodiment, the hafnium transition metal metallocene-type catalyst system has two bulky ligands that are each substituted with a linear or branched, preferably linear, silyl having 3 or more non-hydrogen atoms, preferably 3 to 10 non-hydrogen atoms, most preferably 3 to 5 non-hydrogen atoms, where at least one bulky ligand is a cyclopentadienyl derived ligand, preferably a cyclopentadienyl ring. In a preferred embodiment the bulky ligands of the hafnium transition metal metallocene are both cyclopentadienyl rings at least one of which is substituted with one or more branched or linear silylalkyls having 3 or more non-hydrogen atoms. In one embodiment, the substituent has at least 3 or more non-hydrogen atoms of which at least one is a silicon atom, for example trimethyl silyl alkyl, tributyl silyl alkyl or tripropyl silyl alkyl or even cyclopropyl silyl. Other non-hydrogen substituent atoms include oxygen and/or nitrogen.

It is contemplated that the substituted bulky ligands of the hafnium transition metal metallocene-type catalyst compound of the invention are asymmetrically substituted in terms of additional substituents or types of substituents, and/or unbalanced in terms of the number of additional substituents on the bulky ligands.

Non-limiting examples of hafnocenes of the invention include bis (n-propyl cyclopentadienyl) hafnium dichloride, dimethyl or dihydride, bis (n-butyl cyclopentadienyl) hafnium dichloride or dimethyl, bis (n-pentyl cyclopentadienyl) hafnium dichloride or dimethyl, (n-propyl cyclopentadienyl)(n-butyl cyclopentadienyl) hafnium dichloride or dimethyl, bis[(2-trimethylsilyl-ethyl)cyclopentadienyl] hafnium dichloride or dimethyl, bis(trimethylsilyl cyclopentadienyl) hafnium dichloride or dimethyl or dihydride, bis (2-n-propyl indenyl) hafnium dichloride or dimethyl, bis (2-n-butyl indenyl) hafnium dichloride or dimethyl, dimethylsilyl bis (n-propyl cyclopentadienyl) hafnium dichloride or dimethyl, dimethylsilyl bis (n-butyl cyclopentadienyl) hafnium dichloride or

dimethyl, bis (9-n-propyl fluorenyl) hafnium dichloride or dimethyl, bis (9-n-butyl fluorenyl) hafnium dichloride or dimethyl, (9-n propyl fluorenyl)(2-n-propyl indenyl) hafnium dichloride or dimethyl, bis (1,2- n-propyl, methyl cyclopentadienyl) hafnium dichloride or dimethyl, (n-propyl cyclopentadienyl)(1,3-n-propyl, n-butyl cyclopentadienyl) hafnium dichloride or dimethyl and the like.

In one preferred embodiment the hafnocenes of the invention are unbridged mono- and bis- hafnocenes where a structural bridge is not required for stereorigidity. It is also contemplated that in one embodiment, the hafnocenes of the invention include their structural or optical isomers and mixtures thereof.

For the purposes of this patent specification and appended claims, the term "activator" is defined to be any compound or component which can activate a bulky ligand transition metal metallocene-type catalyst compound as described above, for example, a Lewis acid or a non-coordinating ionic activator or ionizing activator or any other compound that can convert a neutral metallocene catalyst component to a metallocene cation. It is within the scope of this invention to use alumoxane or modified alumoxane as an activator, and/or to also use ionizing activators, neutral or ionic, such as tri (n-butyl) ammonium tetrakis(pentafluorophenyl) boron or a trisperfluorophenyl boron metalloid precursor which ionize the neutral metallocene compound.

There are a variety of methods for preparing alumoxane and modified alumoxanes, non-limiting examples of which are described in U.S. Patent No. 4,665,208, 4,952,540, 5,091,352, 5,206,199, 5,204,419, 4,874,734, 4,924,018, 4,908,463, 4,968,827, 5,308,815, 5,329,032, 5,248,801, 5,235,081, 5,157,137, 5,103,031, 5,391,793, 5,391,529, 5,693,838 and European publications EP-A-0 561 476, EP-B1-0 279 586 and EP-A-0 594-218, and PCT publication WO 94/10180, all of which are herein fully incorporated by reference.

Ionizing compounds may contain an active proton, or some other cation associated with but not coordinated or only loosely coordinated to the remaining ion of the ionizing compound. Such compounds and the like are described in European publications EP-A-0 570 982, EP-A-0 520 732, EP-A-0 495 375, EP-A-0 426 637, EP-A-500 944, EP-A-0 277 003 and EP-A-0 277 004, and U.S. Patent Nos. 5,153,157, 5,198,401, 5,066,741, 5,206,197, 5,241,025, 5,387,568, 5,384,299 and 5,502,124 and U.S. Patent Application Serial No. 08/285,380, filed August 3, 1994, all of which are herein fully incorporated by reference.

Combinations of activators are also contemplated by the invention, for example,

alumoxanes and ionizing activators in combinations, see for example, PCT publications WO 94/07928 and WO 95/14044 and U.S. Patent Nos. 5,153,157 and 5,453,410 all of which are herein fully incorporated by reference

5 In an embodiment of the invention two or more bulky ligand hafnium transition metal metallocene-type catalyst compounds as described above can be combined to form a catalyst system useful in the invention. For example, those mixed catalysts described in U.S. Patent Nos. 5,281,679, 5,359,015 and 5,470,811, all of which are herein fully incorporated herein reference. In another embodiment of the catalyst system of the invention combinations of one or more of catalyst
10 components of the formulas (III) and/or (IV) are contemplated.

In one embodiment, metallocene catalyst components can be combined to form the blend compositions as described in PCT publication W0 90/03414 published April 5, 1990, herein fully incorporated by reference. In yet another embodiment of the invention mixed metallocenes as described in U.S. Patent Nos.
15 4,937,299 and 4,935,474, both are herein fully incorporated herein by reference, can be used to produce polymers having a broad molecular weight distribution and/or a multimodal molecular weight distribution.

In another embodiment of the invention at least one metallocene catalyst of the invention can be combined with a non-metallocene or traditional Ziegler-Natta catalyst or catalyst system, or chromium based catalysts or catalyst systems, non-limiting examples are described in U.S. Patent Nos. 4,159,965, 4,325,837,
20 4,701,432, 5,124,418, 5,077,255, 5,183,867, 5,391,660, 5,395,810 and 5,691,264, all of which are herein fully incorporated by reference.

It is within the scope of this invention that Ni^{2+} and Pd^{2+} complexes described in the articles Johnson, et al., "New Pd(II)- and Ni(II)- Based Catalysts for Polymerization of Ethylene and α -Olefins", J. Am. Chem. Soc. 1995, 117, 6414-6415 and Johnson, et al., "Copolymerization of Ethylene and Propylene with Functionalized Vinyl Monomers by Palladium(II) Catalysts", J. Am. Chem. Soc.,
25 1996, 118, 267-268, and WO 96/23010 published August 1, 1996 which are all herein fully incorporated by reference, can be used as catalysts in combination with the hafnocenes of the invention. These complexes can be either dialkyl ether adducts, or alkylated reaction products of the described dihalide complexes that can be activated to a cationic state by the activators of this invention. It is also within the scope of the process of this invention that the above described
30 complexes can be combined with one or more of the catalyst compounds
35

08986696 "120897"

represented by formula (III) and (IV), with one or more activators, and with one or more of the support materials using one of the support methods that are described below.

5 For purposes of this patent specification the terms "carrier" or "support" are interchangeable and can be any support material, preferably a porous support material, for example, talc, inorganic oxides, inorganic chlorides, and magnesium chloride, and resinous support materials such as polystyrene or polystyrene divinyl benzene polyolefins or polymeric compounds or any other organic or inorganic support material and the like, or mixtures thereof.

10 The preferred support materials are inorganic oxide materials, which include those of Groups 2, 3, 4, 5, 13 or 14 metal oxides. In a preferred embodiment, the catalyst support materials include silica, alumina, silica-alumina, and mixtures thereof. Other inorganic oxides that may be employed either alone or in combination with the silica, alumina or silica-alumina and magnesia, titania, zirconia, and the like.

15 It is preferred that the carrier of the catalyst of this invention has a surface area in the range of from about 10 to about 700 m²/g, pore volume in the range of from about 0.1 to about 4.0 cc/g and average particle size in the range of from about 10 to about 500 μm. More preferably, the surface area is in the range of from about 50 to about 500 m²/g, pore volume of from about 0.5 to about 3.5 cc/g and average particle size of from about 20 to about 200 μm. Most preferably the surface area range is from about 100 to about 400 m²/g, pore volume from about 0.8 to about 3.0 cc/g and average particle size is from about 20 to about 100 μm. The average pore size of the carrier of the invention typically has pore size in the range of from 10 to 1000 Å, preferably 50 to about 500 Å, and most preferably 75 to about 350 Å.

20 The catalyst system of the invention can be made and used in a variety of different ways as described below. In one embodiment the catalyst is unsupported, preferably in liquid form such as described in U.S. Patent Nos. 5,317,036 and 5,693,727 and European publication EP-A-0 593 083, all of which are herein incorporated by reference. In the preferred embodiment, the catalyst system of the invention is supported. Examples of supporting the catalyst system used in the invention are described in U.S. Patent Nos. 4,701,432, 4,808,561, 4,912,075, 4,925,821, 4,937,217, 5,008,228, 5,238,892, 5,240,894, 5,332,706, 5,346,925, 5,422,325, 5,466,649, 5,466,766, 5,468,702, 5,529,965, 5,554,704, 5,629,253,

5,639,835, 5,625,015, 5,643,847 and 5,665,665 and U.S. Application Serial Nos. 271,598 filed July 7, 1994 and 788,736 filed January 23, 1997 and PCT publications WO 95/32995, WO 95/14044, WO 96/06187 and WO 97/02297 all of which are herein fully incorporated by reference.

5 In another embodiment, the catalyst system of the invention contains a polymer bound ligand as described in U.S. Patent No. 5,473,202 which is herein fully incorporated by reference. In one embodiment the catalyst system of the invention is spray dried as described in U.S. Patent No. 5,648,310 which is fully incorporated herein by reference. In an embodiment the support of the invention is
10 functionalized as described in European publication EP-A-0 802 203 or at least one substituent or leaving group is selected as described in U.S. Patent No. 5,688,880, both of which are herein fully incorporated by reference.

In one embodiment of the process of the invention, olefin(s), preferably C₂ to C₃₀ olefin(s) or alpha-olefin(s), preferably ethylene or propylene or
15 combinations thereof are prepolymerized in the presence of the catalyst or catalyst system of the invention prior to the main polymerization. The prepolymerization can be carried out batchwise or continuously in gas, solution or slurry phase including at elevated pressures. The prepolymerization can take place with any alpha-olefin monomer or combination and/or in the presence of any molecular
20 weight controlling agent such as hydrogen. For details on prepolymerization see U.S. Patent Nos. 4,923,833, 4,921,825 and 5,283,278 and European publication EP-B-0279 863 all of which are herein fully incorporated by reference.

In another embodiment of the invention, the supported catalyst system of the invention includes an antistatic agent or surface modifier, for example, those
25 described in U.S. Patent No. 5,283,278 and PCT publication WO 96/11960 which are herein fully incorporated by reference. Non-limiting examples of antistatic agents and surface modifiers include alcohol, thiol, silanol, diol, ester, ketone, aldehyde, acid, amine, and ether compounds. Tertiary amines, ethoxylated amines, and polyether compounds are preferred. The antistatic agent can be added at any
30 stage in the formation of the supported catalyst system of the invention, however, it is preferred that it is added after the supported catalyst system of the invention is formed, in either a slurry or dried state.

A preferred method for producing the catalyst of the invention is described below and can be found in U.S. Application Serial Nos. 265,533, filed June 24,
35 1994 and 265,532, filed June 24, 1994 and PCT publications WO 96/00245 and

08986596-120897

WO 96/00243 both published January 4, 1996, all of which are herein fully incorporated by reference. In a preferred embodiment, the metallocene-type catalyst component is slurried in a liquid to form a metallocene solution and a separate solution is formed containing an activator and a liquid. The liquid can be any compatible solvent or other liquid capable of forming a solution or the like with at least one metallocene catalyst component and/or at least one activator. In the preferred embodiment the liquid is a cyclic aliphatic or aromatic hydrocarbon, most preferably toluene. The metallocene and activator solutions are mixed together and added to a porous support or the porous support is added to the solutions such that the total volume of the metallocene solution and the activator solution or the metallocene and activator solution is less than four times the pore volume of the porous support, more preferably less than three times, even more preferably less than two times; preferred ranges being from 1.1 times to 3.5 times range and most preferably in the 1.2 to 3 times range.

Procedures for measuring the total pore volume of a porous support are well known in the art. Details of one of these procedures is discussed in Volume 1, *Experimental Methods in Catalytic Research* (Academic Press, 1968) (specifically see pages 67-96). This preferred procedure involves the use of a classical BET apparatus for nitrogen absorption. Another method well known in the art is described in Innes, *Total Porosity and Particle Density of Fluid Catalysts By Liquid Titration*, Vol. 28, No. 3, Analytical Chemistry 332-334 (March, 1956).

The mole ratio of the metal of the activator component to the transition metal of the metallocene component is in the range of ratios between 0.3:1 to 1000:1, preferably 20:1 to 800:1, and most preferably 50:1 to 500:1. Where the activator is an aluminum-free ionizing activator such as those based on the anion tetrakis(pentafluorophenyl)boron, the mole ratio of the metal of the activator component to the transition metal component is preferably in the range of ratios between 0.3:1 to 3:1.

In another embodiment the catalyst loading in millimoles (mmoles) of metallocene to weight of support catalyst in grams (g) is in the range of from about 0.001 to about 2.0 mmoles of metallocene per g of support material, preferably from about 0.005 to about 1.0, more preferably from about 0.005 to 0.5 and most preferably from about 0.01 to 0.05.

In one embodiment, the catalyst of the invention has a catalyst productivity of greater than 1000 grams of polymer per gram of the metallocene catalyst,

preferably greater than 1400 grams of polymer per gram of metallocene catalyst, more preferably greater than 1800 grams of polymer per gram of metallocene catalyst, even more preferably greater than 2000 grams of polymer per gram of metallocene catalyst, and most preferably greater than 2500 grams of polymer per gram of metallocene catalyst.

Polymerization Process of the Invention

The substituted bulky ligand hafnium transition metal metallocene-type catalyst compounds and catalyst systems of this invention are suited for the polymerization of monomers, and optionally one or more comonomers, in any polymerization process, solution phase, gas phase or slurry phase, most preferably a gas or slurry phase process is used.

In an embodiment, this invention is directed toward the solution, slurry or gas phase polymerization or copolymerization reactions involving the polymerization of one or more of the monomers having from 2 to 30 carbon atoms, preferably 2-12 carbon atoms, and more preferably 2 to 8 carbon atoms. The invention is particularly well suited to the copolymerization reactions involving the polymerization of one or more of the monomers, for example alpha-olefin monomers of ethylene, propylene, butene-1, pentene-1, 4-methyl-pentene-1, hexene-1, octene-1, decene-1, and cyclic olefins such as cyclopentene, and styrene or a combination thereof. Other monomers can include polar vinyl monomers, diolefins such as dienes, polyenes, norbornene, norbornadiene, acetylene and aldehyde monomers. Preferably a copolymer of ethylene or propylene is produced. Preferably the comonomer is an alpha-olefin having from 3 to 15 carbon atoms, preferably 4 to 12 carbon atoms and most preferably 4 to 8 carbon atoms. In another embodiment ethylene or propylene is polymerized with at least two different comonomers to form a terpolymer and the like, the preferred comonomers are a combination of alpha-olefin monomers having 3 to 10 carbon atoms, more preferably 4 to 8 carbon atoms.

In another embodiment ethylene or propylene is polymerized with at least two different comonomers to form a terpolymer and the like, the preferred comonomers are a combination of alpha-olefin monomers having 3 to 10 carbon atoms, more preferably 3 to 8 carbon atoms, optionally with at least one diene monomer. The preferred terpolymers include the combinations such as ethylene/butene-1/hexene-1, ethylene/propylene/butene-1,

propylene/ethylene/butene-1, propylene/ethylene/hexene-1,
ethylene/propylene/norbornadiene and the like.

In the most preferred embodiment the process of the invention relates to
the polymerization of ethylene and at least one comonomer having from 4 to 8
carbon atoms. Particularly, the comonomers are butene-1, 4-methyl-pentene-1,
hexene-1 and octene-1, the most preferred being hexene-1.

Typically in a gas phase polymerization process a continuous cycle is
employed where in one part of the cycle of a reactor, a cycling gas stream,
otherwise known as a recycle stream or fluidizing medium, is heated in the reactor
by the heat of polymerization. This heat is removed in another part of the cycle by
a cooling system external to the reactor. (See for example U.S. Patent Nos.
4,543,399, 4,588,790, 5,028,670, 5,317,036, 5,352,749, 5,405,922, 5,436,304,
5,453,471, 5,462,999, 5,616,661 and 5,668,228 all of which are fully incorporated
herein by reference.)

Generally, in a gas fluidized bed process for producing polymers, a gaseous
stream containing one or more monomers is continuously cycled through a
fluidized bed in the presence of a catalyst under reactive conditions. The gaseous
stream is withdrawn from the fluidized bed and recycled back into the reactor.
Simultaneously, polymer product is withdrawn from the reactor and fresh
monomer is added to replace the polymerized monomer. The reactor pressure may
vary from about 100 psig (680 kPag) to about 500 psig (3448 kPag), preferably in
the range of from about 200 psig (1379 kPag) to about 400 psig (2759 kPag),
more preferably in the range of from about 250 psig (1724 kPag) to about 350 psig
(2414 kPag). The reactor temperature may vary between about 60°C and about
120°C, preferably about 60°C to about 115°C, and more preferably in the range of
from about 70°C to 110°C, and most preferably in the range of from about 70°C to
95°C. The settled bulk density for the polymers produced by the process of
invention are in the range of from about 10 to 35 lb/ft³ (160 to 561 kg/m³),
preferably from about 12 to 35 lb/ft³ (193 to 561 kg/m³), more preferably from
about 14 to 32 lb/ft³ (224 to 513 kg/m³), and most preferably from about 15 to 30
lb/ft³ (240 to 481 kg/m³).

Other gas phase processes contemplated by the process of the invention
include those described in U.S. Patent Nos. 5,627,242, 5,665,818 and 5,677,375,
and European publications EP-A- 0 794 200, EP-A- 0 802 202 and EP-B- 634 421
all of which are herein fully incorporated by reference.

A preferred process of the invention is where the process, preferably a slurry or gas phase process, most preferably a gas phase process, is operated in the absence of or essentially free of any scavengers, such as triethylaluminum, trimethylaluminum, tri-isobutylaluminum and tri-n-hexylaluminum and diethyl aluminum chloride and the like. This preferred process is described in PCT publication WO 96/08520, which is herein fully incorporated by reference.

A slurry polymerization process generally uses pressures in the range of about 1 to about 50 atmospheres and even greater and temperatures in the range of 0°C to about 200°C. In a slurry polymerization, a suspension of solid, particulate polymer is formed in a liquid polymerization medium to which ethylene and comonomers and often hydrogen along with catalyst are added. The liquid employed in the polymerization medium can be alkane or cycloalkane, or an aromatic hydrocarbon such as toluene, ethylbenzene or xylene. The medium employed should be liquid under the conditions of polymerization and relatively inert. Preferably, hexane or isobutane medium is employed.

In one embodiment a preferred polymerization technique of the invention is referred to as a particle form, or slurry process where the temperature is kept below the temperature at which the polymer goes into solution. Such technique is well known in the art, see for instance U.S. Patent No. 3,248,179 which is fully incorporated herein by reference. The preferred temperature in the particle form process is within the range of about 185°F (85°C) to about 230°F (110°C). Two preferred polymerization methods for the slurry process are those employing a loop reactor and those utilizing a plurality of stirred reactors in series, parallel, or combinations thereof. Non-limiting examples of slurry processes include continuous loop or stirred tank processes. Also, other examples of slurry processes are described in U.S. Patent No. 4,613,484, which is herein fully incorporated by reference.

It is also contemplated in an embodiment of the invention, that the process is a multistage polymerization process where one reactor is operating in slurry phase that feeds into a reactor operating in a gas phase as described in U.S. Patent No. 5,684,097, which is fully incorporated herein by reference.

In one embodiment the reactor utilized in the present invention is capable of producing greater than 500 lbs/hr (227 Kg/hr) to about 200,000 lbs/hr (90,900 Kg/hr) or higher of polymer, preferably greater than 1000 lbs/hr (455 Kg/hr), more preferably greater than 10,000 lbs/hr (4540 Kg/hr), even more preferably greater

than 25,000 lbs/hr (11,300 Kg/hr), still more preferably greater than 35,000 lbs/hr (15,900 Kg/hr), still even more preferably greater than 50,000 lbs/hr (22,700 Kg/hr) and most preferably greater than 65,000 lbs/hr (29,000 Kg/hr) to greater than 100,000 lbs/hr (45,500 Kg/hr).

5 The productivity of the catalyst or catalyst system is influenced by the main monomer partial pressure. The preferred mole percent of the main monomer, ethylene or propylene, preferably ethylene is from about 25 to 90 mole percent and the monomer partial pressure is in the range of from about 75 psia (517 kPa) to about 300 psia (2069 kPa), which are typical conditions in a gas phase
10 polymerization process.

 In another embodiment of the invention where the hafnocene of the invention is in particular an unbridged metallocene-type catalyst, the process of the invention is capable of producing a polymer product having a melt index of less than 0.1 dg/min without the addition of hydrogen to the process.

15 **Polymer Product of the Invention**

 The polymers produced by this invention can be used in a wide variety of products and end-use applications. The polymers typically have a density in the range of from 0.86g/cc to 0.97 g/cc, preferably in the range of from 0.88 g/cc to 0.965 g/cc, more preferably in the range of from 0.900 g/cc to 0.96 g/cc, even
20 more preferably in the range of from 0.905 g/cc to 0.95 g/cc, yet even more preferably in the range from 0.910 g/cc to 0.940 g/cc, and most preferably greater than 0.910 g/cc, preferably greater than 0.915 g/cc. The polymers of the invention typically have a narrow molecular weight distribution, a weight average molecular weight to number average molecular weight (M_w/M_n) of greater than 1.5 to about
25 4, particularly greater than 2 to about 3, more preferably greater than about 2.2 to less than 3. Also, the polymers of the invention typically have a narrow composition distribution. In another embodiment, the polymers produced by the process of the invention, particularly in a slurry and gas phase process, contain less than 2 ppm hafnium, preferably less than 1.5 ppm hafnium, more preferably less
30 than 1 ppm hafnium. In an embodiment, the polymer of the invention contains in the range of from about 0.01 ppm to about 2 ppm hafnium, preferably in the range of from about 0.01 ppm to about 1.5 ppm hafnium, more preferably in the range of from about 0.01 ppm to 1 or less ppm hafnium.

 Polymers produced by the process of the invention are useful in such
35 forming operations as film, sheet, and fiber extrusion and co-extrusion as well as

08986696 "120897"
258027" 9698680

blow molding, injection molding and rotary molding. Films include blown or cast films formed by coextrusion or by lamination useful as shrink film, cling film, stretch film, sealing films, oriented films, snack packaging, heavy duty bags, grocery sacks, baked and frozen food packaging, medical packaging, industrial liners, membranes, etc. in food-contact and non-food contact applications. Fibers include melt spinning, solution spinning and melt blown fiber operations for use in woven or non-woven form to make filters, diaper fabrics, medical garments, geotextiles, etc. Extruded articles include medical tubing, wire and cable coatings, geomembranes, and pond liners. Molded articles include single and multi-layered constructions in the form of bottles, tanks, large hollow articles, rigid food containers and toys, etc.

EXAMPLES

In order to provide a better understanding of the present invention including representative advantages thereof, the following examples are offered.

The properties of the polymer were determined by the following test methods:

Density is measured in accordance with ASTM-D-1238.

MWD, or polydispersity, is a well-known characteristic of polymers. MWD is generally described as the ratio of the weight average molecular weight (Mw) to the number average molecular weight (Mn). The ratio of Mw/Mn can be measured by gel permeation chromatography techniques, or indirectly, by measuring the ratio of I_{21} to I_2 (melt index) as described in ASTM D-1238-F and ASTM D-1238-E respectively.

In all the Examples below the methylalumoxane (MAO) is a 30 weight percent MAO solution in toluene available from Albemarle Corporation, Baton Rouge, Louisiana, the Davison 948 silica is available from W.R. Grace, Davison Chemical Division, Baltimore, Maryland and the N,N-bis(2-hydroxyethyl) octadecylamine is available as Kemamine AS-990 from ICI Specialties, Wilmington, Delaware. The metallocene components of the examples were prepared in accordance with procedures well known in the art.

Example 1

Preparation of Catalyst

A solution of methylalumoxane and metallocene was formed by adding 11 cm³ of 30 wt-% MAO solution in toluene onto 0.202 g of bis (n-propylcyclopentadienyl) hafnium dichloride in a vial. 40 cm³ of fresh toluene was

added, and the mixture stirred for 1 hour at 25°C. This pre-mixed solution of the MAO and the metallocene was then added onto 10 g of Davison 948 silica dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. The final catalyst was then dried to free-flowing powder under vacuum at 65°C.

5 **Polymerization**

 A sample of the dry catalyst formed in the above Example 1 was then used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 155 psig (1069 kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure changes due to polymerization. After 1 h (hour), the polymer formed was separated from the seed bed material and analyzed for the molecular properties shown in Table 1 below as Run 1 and 2.

10 **Example 2**

Preparation of Catalyst

15 A solution of methylalumoxane and metallocene was formed by adding 66.5 cm³ of 30 wt-% MAO solution in toluene onto 1.21 g of bis (n-propylcyclopentadienyl) hafnium dichloride in a vial. 50 cm³ of fresh toluene was added, and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of the MAO and the metallocene was then added onto 60 g of Davison 948 silica dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a solution of 0.41 g of N,N-bis(2-hydroxyethyl) octadecylamine in 50 cm³ toluene was added, and stirring continued for another 30 minutes. The final catalyst was then dried to free-flowing powder under vacuum at 65°C.

20 **Polymerization**

25 A sample of the dry catalyst formed in Example 2 was then used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 158 psig (1089 kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 1 h, the polymer formed was separated from the seed bed material and analyzed for the molecular properties shown as Run 3 in Table 1 below.

30 **Example 3**

Preparation of Catalyst

35 a) Methylalumoxane (1155 cm³ of 30 wt-% solution in toluene) was charged into a 2-gallon reaction vessel. 1970 cm³ of fresh toluene was added. Then a

08986696 "120897

solution of 20.2 g of bis (n-propylcyclopentadienyl) hafnium dichloride in 355 cm³ toluene was added. The temperature was maintained at 27°C and the mixture stirred for 1.5 hour.

- 5 b) 1000 g of a Davison 948 silica dehydrated at 600°C was charged into a 2-gallon reaction vessel at 27°C. The solution of methylalumoxane and metallocene from above was added onto the silica in two equal portions. Then an additional 250 cm³ toluene was added to the slurry. After 1 hour, a solution of 6.7 g of N,N-bis(2-hydroxyethyl) octadecylamine in 70 cm³ toluene was added and stirring continued for another 20 minutes. The final catalyst was
10 then dried to free-flowing powder at 68°C under vacuum.

Polymerization

Samples of the dry catalyst formed in Example 3 each were then used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 158 psig (1089 kPag), was held
15 constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 1 h, the polymer formed was separated from the seed bed material and analyzed for the molecular properties shown as Runs 4-6 in Table 1 below.

Example 4

Preparation of Catalyst

A solution of methylalumoxane and metallocene was formed by adding 27.8 cm³ of 30 wt-% MAO solution in toluene onto 0.536 g of bis (n-butylcyclopentadienyl) hafnium dichloride in a vial. 60 cm³ of fresh toluene was added, and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of
25 the MAO and the metallocene was then added onto 25 g of Davison 948 silica dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a solution of 0.166 g of N,N-bis(2-hydroxyethyl) octadecylamine in 40 cm³ toluene was added, and stirring continued for another 30 minutes. The final catalyst was then dried to free-flowing powder under vacuum at 65°C.

Polymerization

Samples of the dry catalyst formed in Example 4 then were each used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 155 psig (1069 kPag), was held
35 constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 1 h, the polymer formed was

08986696 "120897
268021" 9698680

separated from the seed bed material and analyzed for the molecular properties shown as Runs 7-9 in Table 1 below.

Comparative Example 5

Preparation of Catalyst

5 A solution of methylalumoxane and metallocene was formed by adding
27.7 cm³ of 30 wt-% MAO solution in toluene onto 0.413 g of bis
(cyclopentadienyl) hafnium dichloride in a vial. 50 cm³ of fresh toluene was added,
and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of the
MAO and the metallocene was then added onto 25 g of Davison 948 silica dried to
10 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a solution of
0.166 g of N,N-bis(2-hydroxyethyl) octadecylamine in 40 cm³ toluene was added,
and stirring continued for another 30 minutes. The final catalyst was then dried to
free-flowing powder under vacuum at 65°C.

Polymerization

15 Samples of the dry catalyst formed in Comparative Example 5 were then
each used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch
gas-phase reactor at 85°C. The pressure in the reactor, about 158 psig (1089
kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to
compensate for any pressure change due to polymerization. After 1 h, the polymer
20 formed was separated from the seed bed material and analyzed for the molecular
properties shown as Runs C1 and C2 in Table 1 below.

Comparative Example 6

Preparation of Catalyst

25 A solution of methylalumoxane and metallocene was formed by adding
27.8 cm³ of 30 wt-% MAO solution in toluene onto 0.444 g of bis
(methylcyclopentadienyl) hafnium dichloride in a vial. 60 cm³ of fresh toluene was
added, and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of
the MAO and the metallocene was then added onto 25 g of Davison 948 silica
dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a
30 solution of 0.169 g of N,N-bis(2-hydroxyethyl) octadecylamine in 50 cm³ toluene
was added, and stirring continued for another 30 minutes. The final catalyst was
then dried to free-flowing powder under vacuum at 65°C.

Polymerization

35 A sample of the dry catalyst formed in Comparative Example 6 was then
used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch

gas-phase reactor at 85°C. The pressure in the reactor, about 154 psig (1062 kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for pressure changes due to polymerization. After 1 h, the polymer formed was separated from the seed bed material and analyzed for the molecular properties shown as Run C3 in Table 1 below.

Comparative Example 7

Preparation of Catalyst

A solution of methylalumoxane and metallocene was formed by adding 27.8 cm³ of 30 wt-% MAO solution in toluene onto 0.475 g of bis (ethylcyclopentadienyl) hafnium dichloride in a vial. 60 cm³ of fresh toluene was added, and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of the MAO and the metallocene was then added onto 25 g of Davison 948 silica dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a solution of 0.167 g of N,N-bis(2-hydroxyethyl) octadecylamine in 50 cm³ toluene was added, and stirring continued for another 30 minutes. The final catalyst was then dried to free-flowing powder under vacuum at 65°C.

Polymerization

A sample of the dry catalyst formed above in Comparative Example 7 was then used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 160 psig (1103 kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 1 h, the polymer formed was separated from the seed bed material and analyzed for the molecular properties shown as Run C4 in Table 1 below.

Comparative Example 8

Preparation of Catalyst

A solution of methylalumoxane and metallocene was formed by adding 28 cm³ of 30 wt-% MAO solution in toluene onto 0.585 g of Me₂Si (Indenyl)₂ hafnium dichloride in a vial. 60 cm³ of fresh toluene was added, and the mixture stirred for 1.5 hours at 25°C. This pre-mixed solution of the MAO and the metallocene was then added onto 25 g of Davison 948 silica dried to 600°C. The resulting slurry was stirred for 1.5 hours at 25°C. Then a solution of 0.167 g of N,N-bis(2-hydroxyethyl) octadecylamine in 40 cm³ toluene was added, and stirring continued for another 30 minutes. The final catalyst was then dried to free-flowing powder under vacuum at 65°C.

Polymerization

5 Samples of the dry catalyst formed above in Comparative Example 8 were then each used in a polymerization process of ethylene/1-butene in a 2-liter semi-batch gas-phase reactor at 85°C. The pressure in the reactor, about 158 psig (1089 kPag), was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 1 h, the polymer formed was separated from the seedbed material and analyzed for the molecular properties shown as Runs C5-C7 in Table 1 below.

10 While the present invention has been described and illustrated by reference to particular embodiments, those of ordinary skill in the art will appreciate that the invention lends itself to variations not necessarily illustrated herein. It is contemplated that the catalyst system of this invention can be used in combination with other catalyst systems comprising more than one catalyst system of the invention. For this reason, then, reference should be made solely to the
15 appended claims for purposes of determining the true scope of the present invention.

08986696 "120897

Table 1

Run #	Catalyst (mg)	Polymer Yield (g)	Activity ¹	Density (g/cc)	I ₂ (dg/min)	I ₂₁ (dg/min)	Mw	MWD
			(nPrCp)₂HfCl₂					
1	100	211	2126	0.9061	0.096	2.26	278942	2.88
2	50	117	2363	0.9025	0.089	2.5	275100	2.61
3	50	136	2674	NM	NM	1.83	NM	NM
4	50	159	3159	0.9064	NM	1.76	283282	2.82
5	50	117	2325	0.9091	NM	1.77	272925	2.80
6	50	117	2356	0.9081	NM	2.0	316801	2.88
			(nBuCp)₂HfCl₂					
7	150	271	1821	0.9057	NM	1.2	322890	2.46
8	150	225	1479	0.9056	NM	0.83	NM	NM
9	100	195	1935	0.9070	NM	1.51	NM	NM
			(Cp)₂HfCl₂					
C1	300	12	40	0.9310	NM	0.42	361692	3.98
C2	500	18	36	0.9273	NM	0.67	NM	NM
			(MeCp)₂HfCl₂					
C3	150	17	112	0.9234	NM	0.68	291412	3.24
			(EtCp)₂HfCl₂					
C4	150	16	107	0.9275	NM	0.36	375772	3.20
			Me₂Si(Ind)₂HfCl₂					
C5	150	7	48	0.9365	NM	1.74	232475	3.44
C6	150	6	37	0.9265	NM	1.21	263758	4.16
C7	500	25	49	0.9239	NM	1.73	239161	3.40

Note 1 - - Catalyst activity expressed as $g_{PE} / (g_{CAT} \cdot h \cdot 150 \text{ psi})$


NM - - Not Measured; "Ind" is indenyl

0898656 " 120897
268271" 9698680

CLAIMS

We Claim:

1. A catalyst system comprising a bulky ligand hafnium transition metal metallocene-type catalyst compound, wherein at least one bulky ligand is substituted with a substituent having 3 or more non-hydrogen atoms.
2. The catalyst system in accordance with claim 1 wherein the at least one bulky ligand is substituted with a substituent having 3 or more carbon atoms.
3. The catalyst system in accordance with claim 1 wherein the at least one bulky ligand is substituted with at least one alkyl having 3 or more carbon atoms.
4. The catalyst system in accordance with claim 1 wherein the catalyst compounds comprises two bulky ligands.
5. The catalyst system in accordance with claim 4 wherein at least one bulky ligand is a cyclopentadienyl derived ligand that is substituted with at least one alkyl having 3 or more carbon atoms.
6. The catalyst system in accordance with claim 1 wherein the substituent is selected from one or more of the group consisting of n-propyl, isopropyl, n-butyl, isobutyl and n-pentyl.
7. The catalyst system in accordance with claim 1 wherein the at least one bulky ligand is substituted with at least 3 or more non-hydrogen atoms one of which is a silicon atom.
8. The catalyst system in accordance with claim 1 wherein the bulky ligand hafnium transition metal metallocene-type catalyst compound is represented by the formula:




03986696.120897

wherein $(C_5H_5-d-fR''_d)$ is an unsubstituted or substituted cyclopentadienyl ligand bonded to Hf, wherein at least one $(C_5H_5-d-fR''_d)$ is substituted with at least one R" is an alkyl substituent having 3 or more carbon atoms, each additional R", which can be the same or different is hydrogen or a substituted or unsubstituted hydrocarbyl having from 1 to 30 carbon atoms or combinations thereof or two or more carbon atoms are joined together to form a part of a substituted or unsubstituted ring or ring system having 4 to 30 carbon atoms, R''' is one or more or a combination of the group consisting of carbon, germanium, silicon, phosphorous and nitrogen atoms containing radical bridging two $(C_5H_5-d-fR''_d)$ rings, or bridging one $(C_5H_5-d-fR''_d)$ ring to Hf; each Q which can be the same or different is selected from the group consisting of a hydride, substituted and unsubstituted hydrocarbyl having from 1 to 30 carbon atoms, halogen, alkoxides, aryloxides, amides, phosphides and combination thereof; two Q's together form an alkylidene ligand or cyclometallated hydrocarbyl ligand or other divalent anionic chelating ligand; where g is an integer corresponding to the formal oxidation state of Hf, d is 0, 1, 2, 3, 4 or 5, f is 0 or 1 and e is 1, 2 or 3.

9. The catalyst system of claim 8 wherein d is 1, 2, 3 or 4, e is 2 and f is 0.
10. A process for polymerizing olefin(s) in the presence of a catalyst system comprising a bulky ligand hafnium transition metal metallocene-type catalyst compound having at least one bulky ligand substituted with a substituent having 3 or more non-hydrogen atom, and an activator.
11. The process in accordance with claim 10 wherein the substituent has 3 or more carbon atoms.
12. The process in accordance with claim 10 wherein the bulky ligand is one or more cyclopentadienyl derived ligands, wherein one of the cyclopentadienyl derived ligands is substituted with at least one alkyl having 3 or more carbon atoms.

13. The process in accordance with claim 12 wherein the bulky ligands are two cyclopentadienyl derived ligands each substituted with at least one alkyl substituent having 3 or more carbon atoms.
14. The process in accordance with claim 10 wherein the substituent is selected from one or more of the group consisting of n-propyl, isopropyl, n-butyl, isobutyl and n-pentyl.
15. The process in accordance with claim 10 wherein at least one bulky ligand is substituted with at least 3 or more non-hydrogen atoms one of which is a silicon atom.
16. The process in accordance with claim 10 wherein the olefin(s) are alpha-olefins having from 2 to 12 carbon atoms.
17. The process in accordance with claim 10 wherein the olefin(s) are ethylene in combination with one or more other alpha-olefins having from 3 to 10 carbon atoms.
18. The process in accordance with claim 10 wherein the process is a gas phase process.
19. The process in accordance with claim 10 wherein the catalyst system further comprises a support.
20. The process in accordance with claim 10 wherein the bulky ligand hafnium transition metal metallocene-type catalyst compound is bis(n-propyl-cyclopentadienyl) hafnium dichloride.
21. A continuous gas phase process for polymerizing olefin(s) in a fluidized bed gas phase reactor in the presence of a catalyst system to produce a polymer product, the catalyst system comprising a bulky ligand hafnium transition metal metallocene-type catalyst compound having at least one bulky ligand substituted with a substituent having 3 or more carbon atoms, and the polymer product comprising less than 2 ppm hafnium.


22. The process of claim 21 wherein the polymer product comprises less than 1 ppm hafnium.
23. The process in accordance with claim 21 wherein the catalyst system is supported.
24. The process in accordance with claim 21 wherein the substituent is an alkyl having 3 to 10 carbon atoms.
25. The process in accordance with claim 21 wherein the polymer product has a density greater than 0.915 g/cc.
26. The process in accordance with claim 21 wherein the olefin(s) are ethylene and at least one alpha-olefin having 3 to 8 carbon atoms.
27. The process in accordance with claim 21 wherein the catalyst system is represented by the formula:



wherein $(C_5H_5-d-fR''_d)$ is an unsubstituted or substituted cyclopentadienyl ligand bonded to Hf, wherein at least one $(C_5H_5-d-fR''_d)$ is substituted with at least one R'' is an alkyl substituent having 3 or more carbon atoms, each additional R'' , which can be the same or different is hydrogen or a substituted or unsubstituted hydrocarbyl having from 1 to 30 carbon atoms or combinations thereof or two or more carbon atoms are joined together to form a part of a substituted or unsubstituted ring or ring system having 4 to 30 carbon atoms, R''' is one or more or a combination of the group consisting of carbon, germanium, silicon, phosphorous and nitrogen atoms containing radical bridging two $(C_5H_5-d-fR''_d)$ rings, or bridging one $(C_5H_5-d-fR''_d)$ ring to Hf, each Q which can be the same or different is selected from the group consisting of a hydride, substituted and unsubstituted hydrocarbyl having from 1 to 30 carbon atoms, halogen, alkoxides, aryloxides, amides, phosphides and combination thereof; two Q's together form an alkylidene ligand or cyclometallated hydrocarbyl ligand or other divalent anionic chelating ligand; where g is an integer

corresponding to the formal oxidation state of Hf, d is 0, 1, 2, 3, 4 or 5, f is 0 and e is 1, 2 or 3, and the polymer product has a melt index less than 0.1 dg/min without the addition of hydrogen to the process.

28. A continuous slurry phase process for polymerizing olefin(s) in the presence of a catalyst system to produce a polymer product in a liquid polymerization medium, the catalyst system comprising a bulky ligand hafnium transition metal metallocene-type catalyst compound having at least one bulky ligand substituted with a substituent having 3 or more carbon atoms, and the polymer product comprising less than 2 ppm hafnium.
29. The process in accordance with claim 28 wherein the polymer product comprises less than 1 ppm hafnium.
30. The process in accordance with claim 28 wherein the density is greater than 0.900 g/cc.
31. The process in accordance with claim 28 wherein the olefins are ethylene and at least one alpha-olefin having 3 to 8 carbon atoms.
32. The process in accordance with claim 28 wherein the catalyst system is represented by the formula:



wherein $(C_5H_5-d-fR''_d)$ is an unsubstituted or substituted cyclopentadienyl ligand bonded to Hf, wherein at least one $(C_5H_5-d-fR''_d)$ is substituted with at least one R'' is an alkyl substituent having 3 or more carbon atoms, each additional R'' , which can be the same or different is hydrogen or a substituted or unsubstituted hydrocarbyl having from 1 to 30 carbon atoms or combinations thereof or two or more carbon atoms are joined together to form a part of a substituted or unsubstituted ring or ring system having 4 to 30 carbon atoms, R''' is one or more or a combination of the group consisting of carbon, germanium, silicon, phosphorous and nitrogen atoms containing radical bridging two $(C_5H_5-d-fR''_d)$ rings, or bridging one $(C_5H_5-d-fR''_d)$ ring to Hf; each Q which can be the same or different is

selected from the group consisting of a hydride, substituted and unsubstituted hydrocarbyl having from 1 to 30 carbon atoms, halogen, alkoxides, aryloxides, amides, phosphides and combination thereof; two Q's together form an alkylidene ligand or cyclometallated hydrocarbyl ligand or other divalent anionic chelating ligand; where g is an integer corresponding to the formal oxidation state of Hf, d is 0, 1, 2, 3, 4 or 5, f is 0 and e is 1, 2 or 3, and the polymer product has a melt index less than 0.1 dg/min without the addition of hydrogen to the process.

33. A polymer produced with a hafnocene catalyst system, the polymer comprising ethylene and having a hafnium content in the range of 0.1 to 1 ppm.
34. The polymer in accordance with claim 33 wherein the polymer further comprises an alpha-olefin having from 3 to 10 carbon atoms.
35. The polymer in accordance with claim 33 wherein the polymer has a density greater than 0.915 g/cc.
36. A polyethylene polymer produced with a hafnocene catalyst system, the polymer having a density in the range of 0.865 to 0.97 g/cc, a Mw/Mn in the range of between 2 to 3 and a hafnium content of less than 2 ppm.
37. The polymer in accordance with claim 36 wherein the polymer has a hafnium content less than 1 ppm.
38. The polymer in accordance with claim 36 wherein the polymer has a melt index less than 3 dg/min.
39. The polymer in accordance with claim 36 wherein the polymer has a settled bulk density in the range of 15 to 30 lb/ft³ (240 to 481 kg/m³).
40. The polymer in accordance with claim 36 wherein the polymer is a homopolyethylene having a density greater than 0.950 g/cc.

41. The polymer in accordance with claim 36 wherein the polymer contains a support material selected from the group consisting of silica, alumina, and magnesium.
42. The polymer in accordance with claim 36 wherein the hafnocene catalyst system contains a mole ratio of aluminum to hafnium in the range of 50:1 to 500:1.
43. The polymer in accordance with claim 36 wherein the polymer has in the range of between 0.03 to 100 ppm aluminum.
44. The polymer in accordance with claim 36 wherein the hafnocene catalyst system is unbridged.
45. An ethylene based polymer produced by a catalyst system comprising a bulky ligand hafnium transition metal metallocene-type catalyst compound, wherein at least one bulky ligand is substituted with a substituent having 3 to 5 carbon atoms, the polymer having a settled bulk density in the range from 15 to 30 lb/ft³ (240 to 481 kg/m³), a Mw/Mn in the range of from 2 to 3, a density in the range of from 0.900 g/cc to greater than 0.97 g/cc and a hafnium content in the range of from 0.1 to 1 ppm.
46. The polymer in accordance with claim 45 wherein the polymer has a density greater than 0.915 g/cc and a melt index less than 1 dg/min.
47. The polymer in accordance with claim 45 wherein the polymer is selected from the group consisting of an ethylene/butene-1 copolymer, an ethylene/4-methyl-1-pentene copolymer, an ethylene/hexene-1 copolymer and an ethylene/octene-1 copolymer.
48. The polymer in accordance with claim 45 wherein the substituent is a linear alkyl.
49. The polymer in accordance with claim 45 wherein the polymer comprises a support material.

08986656 120397

50. The polymer in accordance with claim 45 wherein the polymer contains in the range of from 0.03 to 100 ppm aluminum.

0898696-120397

POLYMERIZATION CATALYST SYSTEMS AND ITS USE

ABSTRACT

The present invention relates to a process for the polymerization of monomers utilizing a bulky ligand hafnium transition metal metallocene-type catalyst compound, to the catalyst compound itself and to the catalyst compound in combination with an activator.

* * * * *

08986696 120897

DECLARATION FOR PATENT APPLICATION

Case Docket No. 97U001

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Polymerization Catalyst System And Their Use

the specification of which is attached hereto unless the following box is checked:

[] was filed on _____ as Application Serial No. or PCT International Application No. _____ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate(s), or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application(s) for patent or inventor's certificate(s), or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Claimed

_____	_____	_____	[]	[]
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No

I hereby claim the benefit under 35 U.S.C. § 119(e)(1)-(2) of any United States provisional application(s) listed below.

_____	_____
(Application Number)	(Filing Date)

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose material information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

_____	_____	_____
(Application Serial No.)	(Filing Date)	(Status - patented, pending, abandoned)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

NAMES	REGISTRATION NUMBERS
Jaime Sher	34,726
Richard Phillips	30,097

SEND CORRESPONDENCE TO:	DIRECT TELEPHONE CALLS TO:
Exxon Chemical Company	(Name and Telephone Number)
Law Technology	Jaime Sher
P.O. Box 2149	(281) 834-1832
Baytown, Texas 77522-2149	Facsimile No. (281) 834-2495

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

FULL NAME OF INVENTOR	LAST NAME	FIRST NAME	MIDDLE NAME
	Jejelowo	Moses	Olukayode
RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	Kingwood	Texas	Nigerian
POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE OR COUNTRY
	3410 Park Springs	Kingwood	Texas
			ZIP CODE
			77345

Inventor's signature

M. A. Jejelowo

Date

12/8/97

FULL NAME OF INVENTOR	LAST NAME	FIRST NAME	MIDDLE NAME
	Kao	Sun	Chueh
RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	Belle Mead	New Jersey	United States of America
POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE OR COUNTRY
	7 Durham Court	Belle Mead	New Jersey
			ZIP CODE
			08502

Inventor's signature

Date

FULL NAME OF INVENTOR	LAST NAME	FIRST NAME	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE OR COUNTRY
			ZIP CODE

Inventor's signature

Date